



MAXITHEN®

PP Range

for Transparent Colouring

PP-Transparent Colouring

Product MAXITHEN®			Dos	Heat Stability	Light- fastness	Warpage	Polymer
PP	213017	Yellow	3%	260°C	7-8	F3	PPHD 120MO
PP	215137	Yellow	3%	260°C	6	F1	PPHD 120MO
PP	35197	Orange	3%	250°C	6	F1	PPHD 120MO
PP	35647/12	Orange	3%	300°C	6	F1	PPHD 120MO
PP	35657/12	Orange	3%	290°C	7	F1	PPHD 120MO
PP	419077	Red	3%	280°C	6	F1	PPHD 120MO
PP	419087	Red	3%	280°C	6	F1	PPHD 120MO
PP	414677	Red	3%	290°C	7	F1	PPHD 120MO
PP	419617	Red	3%	300°C	7	F3	PPHD 120MO
PP	515857	Blue	3%	280°C	7-8	F3	PPHD 120MO
PP	518607/12	Blue	3%	300°C	7-8	F1	PPHD 120MO
PP	521297/12	Blue	3%	300°C	8	F1	PPHD 120MO
PP	615247	Green	3%	300°C	7-8	F3	PPHD 120MO
PP	616297	Green	3%	260°C	6	F3	PPHD 120MO
PP	620577/12	Green	3%	290°C	6	F1	PPHD 120MO
PP	95737	Black	3%	300°C	8	F1	PPHD 120MO

Dos: Dosage Rate - values in %
Heat Stability: values in °C
Lightfastness: Woolscale 1-8; 8 = best value
Warpage: Rating F1-F3:
 F1: low influence on final article expected
 F2: moderate influence on final article expected
 F3: strong influence on final article expected

All products are:
 Food approved in Germany/Austria
 Free of pigments based on toxic heavy metals
 Free of diarylid pigments

Due to low pigment concentration the values for Heat Stability and Lightfastness must be considered as guidelines only and have to be therefore tested under practical conditions.

Contacts

Gabriel-Chemie Gesellschaft m.b.H.

Industriestrasse 1
A-2352 Gumpoldskirchen
T +43 (0)2252 / 636 30-0
F +43 (0)2252 / 627 25-0
www.gabriel-chemie.com
info@gabriel-chemie.com

Gabriel-Chemie UK LTD

Transfesa Road
Paddock Wood. Kent, TN 12 6 UT
T +44 (0)1892 / 83 65 66
F +44 (0)1892 / 83 69 79
info@uk.gabriel-chemie.com

Gabriel-Chemie Bohemia s.r.o.

K Lihovaru 172
CZ-533 41 Lázně Bohdaneč
T +420 46 / 604 92 01
F +420 46 / 604 92 04
info@cz.gabriel-chemie.com

Gabriel-Chemie France

269/287 rue de la Garenne
F-92000 Nanterre
T +33 (0)1 / 72 69 01 88
F +33 (0)1 / 72 71 84 84
info@fr.gabriel-chemie.com

Gabriel-Chemie Polska sp. z o.o.

Parzniewska 4
PL-05 804 Pruszków
T +48 (0)22 / 738 64 00
F +48 (0)22 / 738 64 01
info@pl.gabriel-chemie.com

OOO Gabriel-Chemie RUS

poc. Dorohovo, Ruzsky raion
Moskovskaya st. d.8
RU-143160 Russia
T +7 495 737 62 36
F +7 495 737 62 36
info@ru.gabriel-chemie.com

Gabriel-Chemie Deutschland GmbH

Ritzenschattenhalb 1
D-87480 Weitnau/Oberallgäu
T +49 (0)8375 / 9201-0
F +49 (0)8375 / 9201-30
info@de.gabriel-chemie.com

Gabriel-Chemie Schweiz AG

Kirchstrasse 17
CH-8274 Gottlieben
T +41 (0)71 / 666 60 90
F +41 (0)71 / 666 60 99
info@ch.gabriel-chemie.com

Gabriel-Chemie Hungária Kft.

Debreceni ut 269
H-4400 Nyiregyhaza
T +36 42 / 594 080
F +36 42 / 594 081
info@hu.gabriel-chemie.com

Gabriel-Chemie Romania S.R.L

P.O. Box O.P.16 – C.P.06
Bucuresti, Romania
T +40 72 / 2434 357
F +40 31 / 4024 027
info@ro.gabriel-chemie.com

Our net of AGENTS and DISTRIBUTORS is listed on our website:
www.gabriel-chemie.com