

VALOX™ RESIN 4031

REGION EUROPE

DESCRIPTION

VALOX 4031 is a 30% high strength glass fibre reinforced PBT injection moulding resin with excellent strength, stiffness and heat resistance. Applications: appliance handles, spotlights, electric motors.

TYPICAL PROPERTY VALUES

Revision 20190709

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	140	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	140	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	10000	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	190	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	190	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7900	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	135	MPa	ISO 527
Tensile Stress, break, 5 mm/min	135	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	10000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	210	MPa	ISO 178
Flexural Stress, break, 2 mm/min	200	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3	%	ISO 178
Flexural Modulus, 2 mm/min	8300	MPa	ISO 178
Ball Indentation Hardness, H358/30	125	MPa	ISO 2039-1
Hardness, Rockwell R	125	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	65	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	60	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	880	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	880	J/m	ASTM D4812
Izod Impact, notched, 23°C	100	J/m	ASTM D256
Izod Impact, notched, 0°C	100	J/m	ASTM D256
Izod Impact, notched, -30°C	100	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	55	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	11	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	12	kJ/m ²	ISO 179/2C

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m²	ISO 179/1eA
Charpy Impact, notched, -30°C	12	kJ/m²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	50	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	55	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	215	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	3.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.2E-04	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	1.98E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.73E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/120	215	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	220	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	210	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Af
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	140	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.54	-	ASTM D792
Filler Content	30	%	ASTM D229
Mold Shrinkage on Tensile Bar, flow	0.3 – 0.7	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.5 – 1	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	50	g/10 min	ASTM D1238
Density	1.54	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.26	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	12	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	30	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	40	cm³/10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	150	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Dielectric Strength, in oil, 0.8 mm	26	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	ASTM D149
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ω .cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0016	-	IEC 60250
Dissipation Factor, 1 MHz	0.014	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-236594	-	-
UL Recognized, 94HB Flame Class Rating	0.84	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	6	mm	UL 94
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.